

(Page 30, Table 3):

TABLE 3

Sub C1

B1

Materials		Example No.				Comparative Example No.			
		1	2	3	4	1	2	3	4
(A)	a	60	60	-	-	60	60	60	-
	b	-	-	60	60	-	-	-	60
(C)	Nonylphenoxy- octa(ethylenoxy) acrylate	10	10	10	10	-	-	-	-
	Nonylphenoxyethylenoxy acrylate	-	-	-	-	10	-	-	-
	EO, PO-modified urethane dimethacrylate ¹	10	-	10	-	10	10	10	10
	β -hydroxypropyl- β' - methacryloyloxyethyl o-phthalate	-	-	-	-	-	10	-	-
	2,2-bis[methacryloxy- pentaethoxy)phenyl]-propane	20	30	20	30	20	20	20	30

¹: A compound of the general formula (IV) wherein R⁷ and R⁸ each are a methyl group, X¹ and X² each are an ethylenoxy group, Y¹ and Y² each are an isopropyleneoxy group, Z³ is a hexylene group, p and q each are 1, and r and v each are 9.

(Page 32, Table 4):

TABLE 4

B2

	Adhesiveness	Scumming
Example 1	20	No
Example 2	25	No
Example 3	30	No
Example 4	35	No
Comp. Example 1	20	Scummed
Comp. Example 2	20	Scummed
Comp. Example 3	20	Scummed
Comp. Example 4	30	Scummed

TC 1700 MAIL ROOM

FEB 11 2003

RECEIVED